

### Product Description

Matt 1 component polyurethane / acrylic floor varnish for light wood types like pine, beech and oak.  
The product can be used in homes, where an matt treatment that can withstand normal wear and tear is desired.

### Directions for use

The floor must be clean, dry and free of soap residue, wax and other contaminants.  
After washing may the surface be neutralized with acetic acid if need be. (31% acetic acid mixed with water in the ratio of 3 dl. acetic acid for 10 litres of water).  
Final sanding before painting should be made with grain 120 and the grinding of grain 150th  
After sanding please, remove dust carefully, possibly by vacuuming.  
You should always perform the test field.

### Cleaning instructions

Cleaning with clean water, preferably added a little detergent, immediately after use.

### Safety & environment

Brush / Roller: Working close, PU-gloves and protective glass.  
Spray: Protective clothing, PU-gloves and shield. A2P3 mask, with air supply when needed.  
Sanding: Working clothes, PU-gloves and protective glass. P2 mask with air supply when needed.  
Further information and MSDS on [www.bj.dk](http://www.bj.dk)

### Remarks

The lacquer is shaken well before use and should always be carried out test field where adhesion is controlled.  
After varnishing the floor can be walked cautiously after about 8 hours, and fully dry after approximately 72 hours.  
Laying of carpet and floor cleaning should only be done after 5-7 days.

Daily cleaning should be done by vacuum cleaning or wash with lukewarm water with a neutral detergent.

### Technical data

<b>Binder:</b>	Acrylic / Polyurethane Aqueous
<b>Type:</b>	
<b>Gloss:</b>	
<b>Vol. dry:</b>	Approx. 30%
<b>Colours:</b>	Clear
<b>Drying:</b>	About 2 hours, overcoatable after approx. 4 hours, you can walk on it after approx. 8 hours and fully cured after 5-7 days (+ 20 ° C, RH: 60%)
<b>Application:</b>	+10 °C to + 25° C. RH: 40-80%
<b>Thinning:</b>	Water
<b>Coverage:</b>	Approx. 10 m <sup>2</sup> /ltr on planed wood
<b>Tools:</b>	Short nap roller or brush
<b>Mal-Code:</b>	00-1 (1993)

