# 554 SECU Wood Oil T030



# Product information

# Beck & Jorgensen A/S

### **Product Description**

Traditional wood-drying oil for new treatment and maintenance of wooden decking, garden furniture and the like. In pressure-treated wood and hard woods.

Wood oil has a good penetration into the wood and creates a water repellent surface that stabilizes and prevents shrinkage cracks in the wood.

Contains active UV filter against the sun's harmful rays and special water-repellent waxes.

For exterior wood surfaces of tropical woods such as Meranti, Sipo, Iroko and Others as well as, for example, Oak, Cedar and impregnated Pine, Spruce and Larch for exterior cladding, garden furniture, wood chips, carports, sheds and the like.

#### **Directions for use**

The wood must be clean, dry and sustainable. The substrate must also be sucking and without previous treatments of varnish, paint and the like.

Weathered wood such as Spruce, Pine and Larch must be cleaned with appropriate cleaner.

Weathered hardwood such as Teak, Mahogany, and the like sanded to fresh wood.

Contaminated surfaces must clean with appropriate cleaner.

Apply the Wood oil with a sponge, brush or roller. Repeat the treatment until the wood aperies uniformly and saturated, however, without forming surface film.

Retreatment is usually 1-2 times a year or as needed.

Contains agents that protect the surface against fouling. For exterior use only.

Degrease very oily woods such as Teak and Iroko by wipping the surface with white spirit before treatment with wood oil.

### Cleaning instructions

White Spirit or "Brush Cleaner"

## Safety & environment

Personal protection equipment must be used. For information regarding safety, health and environment see Material Safety Data Sheet (MSDS) at www.bj.dk.

#### Remarks

The product should not be used without the addition of pigment.

#### **Technical data**

Binder: Alkyd resin Type: Wood Oil

Gloss:

Vol. dry: Approx. 19%

**Colours:** Clear, can be tinted in transparent shades

**Drying:** 6-8 hours, recoatable after 12 hours at 20 ° C and 65% RH

**Application:** +5° C to +25° C. RF: 40-80%

**Thinning:** Should not be thinned

Coverage: 5-10 m<sup>2</sup>/ltr. Depending on the absorption

Tools: Brush, cloth or sponge

Mal-Code:

Rev. date: 11.02.2013 - 1

Page: 1/1