

Product information

Beck & Jorgensen A/S

Product Description

Vådrumsmaling 738 is based on an advanced acrylic binder for humid rooms, industrial kitchens, factories and the pharmaceutical industry.

The product is suitable for concrete, gypsum board, plaster etc.

The paint gives a strong and resistant surface and a part of B&J Bathroom system. Information on www.bj.dk

Contains materials, that protect the film against surface mold.

Directions for use

The substrate must be clean, dry and sound / stable and free from all substances that may prevent good adhesion. Remove dirt, dust and loose material. Wash down previously painted surfaces with appropriate detergent. Priming of porous and water absorbing surfaces with Microprimer 716 or semilar is recommended.

Cleaning instructions

Cleaning with clean water, preferably added a little detergent, immediately after use.

Safety & environment

Brush / Roller: Working close, PU-gloves and protective glass. Spray: Protective clothing, PU-gloves and shield. A2P3 mask, with air supply when needed. Sanding: Working clothes, PU-gloves and protective glass. P2 mask with air supply when needed. Further information and MSDS on www.bj.dk

Remarks

For futher working instructions, please contact B&J Tecnical Department. Use eyeprotection and mask when sanding.

Sprayguide

| Spraying | Nozzle | Air pressure | Ass. Air | Filter |
|--------------------|---------------|--------------|----------|--------|
| Airless and roller | 17-21 (Graco) | | | 60mesh |

Technical data

| Binder: | Acrylic |
|--------------|--|
| Туре: | Acryllic wall paint |
| Gloss: | Approx. 40 Semi gloss |
| Vol. dry: | Aprox 38% |
| Colours: | |
| Drying: | 2-4 hours, recoatable after approx. 12 hours at +20 °C og 65% RF |
| Application: | +10 °C to + 25° C. RH: 40-80% |
| Thinning: | Water. Normally not to be diluted |
| Coverage: | Approx. 10 m ² /ltr on planed wood |
| Tools: | Brush, roller or airless |
| Mal-Code: | 00-1 (1993) |



Rev. date: 15.01.2020 -

This product information is based on both practical and laboratory tests and is a guidance to choice of product and working method. Always use the latest version of the product information, which can be found on www.bj.dk. As we don't know about the workers working conditions, we do not bear responsibility for the final result.

Page: 1/1