

Product Description

Semi transparent aqueous wood stain for outdoor use. For treatment of surfaces such as windows, doors and other exterior surfaces of wood, which also required good durability and simple maintenance.

Product Features

- Protects the surface film against surface mould.
- Contains UV filters to protect the film against the damaging UV beams
- Good load capacity and block resistance.
- Very good durability
- Can be tinted in transparent shades
- Developed for European conditions

Directions for use

753 B3 Water-borne Woodstain Is thoroughly stirred before and during use. The substrate has to be clean and dry. Knots, resinous areas are degreased with cellulose thinner. 753 B3 Water-borne Woodstain should be applied in a full flowing coat, laying off in the direction of the grain, using a minimum number of brush strokes necessary to produce an acceptable finish. It is important for the drying time, to apply in thin layers. The coating has to be carried out during a stable period of dry weather and not in direct sunlight. Pressure impregnated and vacuum impregnated wood does not need any pretreatment.

Maintenance:

The wood has to be dry and clean. Resin exudation has to be removed and degreased with cellulose thinner. Surface mould should be removed and patch primed with 753 B3 Waterborne Woodstain. Coatings in poor condition should be removed completely. If excessive weathering has occurred giving exposed timber a grey appearance, the surface must be thoroughly sanded back to clean, bright timber and then treated first with translucent water-borne wood preserver until saturation. After 24 hours of drying applied 753 B3 Waterborne Woodstain.

Cleaning instructions

Cleaning with clean water, preferably added a little detergent, immediately after use.

Safety & environment

Technical data

Binder:	Alkyd emulsion
Type:	Woodstain, Semi transparent
Gloss:	Approx. 30, semigloss
Vol. dry:	Approx. 30%
Colours:	Clear, can be tinted in transparent shades
Drying:	2-4 hours, recoatable after approx 24 hours at 20 °C 60% RF
Application:	+10 °C to + 25° C. RH: 40-80%
Thinning:	Water. Normally not to be diluted
Coverage:	Rough saw timber: 2-5 m ² /Liter Planed timber: 8-10 m ² /Liter
Tools:	Brush, Roller or Spraying
Mal-Code:	00-1 (1993)



753 B3 Water-borne Woodstain, semi-transp.



Product information

Beck & Jorgensen A/S

Brush / Roller: Working close, PU-gloves and protective glass.

Spray: Protective clothing, PU-gloves and shield. A2P3 mask, with air supply when needed.

Sanding: Working clothes, PU-gloves and protective glass. P2 mask with air supply when needed.

Further information and MSDS on www.bj.dk

Remarks

The moisture content of free-standing wood and ventilated clothing max. 18%