

755 B3 Woodprotection Opaque WB



Product information

Beck & Jørgensen A/S

Product Description

Waterborne woodprotection for exterior joinery. The product is opaque and slightly thixotropic, and a perfect product for shift of colour and long maintenance.

Contains materials, that protect the film against surface mold.

Directions for use

Exterior woodwork, which needs protection against wood-destroying fungus, should be primed prior to treatment with the final product with an appropriate preservative.

Pressure and vacuum impregnated wood of good sound quality can be treated directly after drying with the described product. If need be degrease Resin and knots with an appropriate thinners. Saturate end grain thoroughly with an appropriate preservative.

Maintenance

The substrate must be clean, dry and sustainable. Remove surface fouling with appropriate cleaner. Areas of bare wood are prepared and primed with appropriate primer. Sand glossy surfaces prior to application of the described product. Apply 2-3 rich coats for final protection.

Cleaning instructions

Cleaning with clean water, preferably added a little detergent, immediately after use.

Safety & environment

Brush / Roller: Working close, PU-gloves and protective glass.

Spray: Protective clothing, PU-gloves and shield. A2P3 mask, with air supply when needed.

Sanding: Working clothes, PU-gloves and protective glass. P2 mask with air supply when needed.

Further information and MSDS on www.bj.dk

Remarks

Moisture content of the windows must be 12 + - 3% in freestanding wood and ventilated cladding max. 18%.

Technical data

Binder:	Combination of acrylic and alkyd
Type:	Waterbased Woodprotection
Gloss:	Approx. 30, semigloss
Vol. dry:	App. 35%
Colours:	White and B3 colourcard
Drying:	2-4 hours, recoatable after approx 24 hours at 20 °C 60% RF
Application:	+10 °C to + 25° C. RH: 40-80%
Thinning:	Water. Normally not to be diluted
Coverage:	Rough saw timber: 2-5 m ² /Liter. Planed timber: 8-10 m ² /Liter
Tools:	Brush, Roller or Spraying
Mal-Code:	00-1 (1993)

