

### Product Description

Alkyd primer for interior use with stainbloking effect.

### Directions for use

The substrate must be clean, dry and sustainable. Soiled surfaces should be cleaned with an appropriate cleaner. New wood should be primed once diluted with 1015% turpentine 2. coat to be painted undiluted. The primer must be coated with appropriate enamel, solvent- or water borne. Previously painted surfaces are prepared if necessary with filling and undercoat before the top paints. Iron and metal must be primed with suitable primer.

### Cleaning instructions

White Spirit or "Brush Cleaner"

### Safety & environment

Brush / Roller: Working close, Nitrill-gloves and protective glass and A2 mask.  
Spray: Protective clothing, PU-gloves and shield. A2P3 mask, with air supply when needed.  
Sanding: Working clothes, PU-gloves and protective glass. P2 mask with air supply when needed.  
Further information and MSDS on [www.bj.dk](http://www.bj.dk)

### Technical data

<b>Binder:</b>	Alkyd
<b>Type:</b>	Alkyd primer
<b>Gloss:</b>	Approx 2, Dull matt
<b>Vol. dry:</b>	
<b>Colours:</b>	White
<b>Drying:</b>	6-8 hours, recoatable after 24 hours at 20 ° C 65% RH
<b>Application:</b>	+5° C to +25° C. RF: 40-80%
<b>Thinning:</b>	White spirit
<b>Coverage:</b>	8-10 m <sup>2</sup> /ltr
<b>Tools:</b>	Short nap roller or brush
<b>Mal-Code:</b>	2-1 (1993)