

Product Description

Water-borne translucent slightly thixotropic wood treatment based on aqueous alkyd.

Product description

- Contains agents which protect the film against fouling
- Enhances the natural structure and protects against moisture and cracking
- Contain UV absorber that along with the pigmentation protects against the sun's harmful beams ultraviolet.
- Should not be used as colorless

Directions for use

The humidity of the wood should not exceed 20%.

The surface must be dry, clean and free from resin exudation or any other foreign body, which may counteract perfect adhesion and drying.

Exterior wood species that tends to be degraded by rot should be impregnated according to the relevant use class of BS EN 599, e.g. by treatment with 902 DK-1 Wood Preservative Type 102, prior to the application of Type 121.

Timber joinery, which has been given a preservative treatment by double-vacuum, must have evaporated/dried to a max retention of 25%.

Minimum 2 coats should be applied to ensure satisfactory durability.

Cleaning instructions

Clean the instruments with clean water, preferably added a little detergent, immediately after use.

Safety & environment

Personal protection equipment must be used. For information regarding safety, health and environment see Material Safety Data Sheet (MSDS) at www.bj.dk.

Technical data

Binder: Oil emulsion

Type:

Gloss: Approx. 30, semigloss

Vol. dry: Approx. 22%

Colours:

Drying: 1-2 hours, recoatable after approx. 16 hours at 20 ° C 65% RH.

Application: +20°C to +25°C. RF: 50-75%

Thinning: Water. Normally not to be diluted

Coverage: 5-10 m²/ltr. Depending on the absorption

Tools: Brush, Roller or Spraying

Mal-Code: