

Product Description

Water-based acrylic primer for interior wood and wood-based materials.

Product Features:

Provides good adhesion
Fast drying
Extremely easy to sand
Very good base coat for LARCO interior enamels

Directions for use

Surface must be clean firm and coherent.
Wood humidity should not exceed 20% RH.
Any resin secretions must be removed by scraping and then cleaned with a suitable solvent.
Knots should be sealed with a suitable knot sealer.
Product must be stirred thoroughly and dilute if necessary with water to spray viscosity.
Must be finished with 976 DK Enamel T236.
Recommended wet filmthickness: App. 150 micron.

Cleaning instructions

Clean with water immediately after use. Once a week clean the equipment using an appropriate cleaning agent.

Safety & environment

Personal protection equipment must be used. For information regarding safety, health and environment see Material Safety Data Sheet (MSDS) at www.bj.dk.

Sprayguide

| Spraying | Nozzle | Air pressure | Ass. Air | Filter |
|-----------|---------|--------------|----------|----------|
| Airless | 0,28 mm | 150 bar | | 100 Mesh |
| Airmix | 0,28 mm | 80-90 bar | 1-2 bar | 100 Mesh |
| HVLP usw. | 0,28 mm | 80-90 bar | 1-2 bar | 100 Mesh |

Technical data

Binder: Acrylic
Type:
Gloss: Approx. 3 Flat matt
Vol. dry: Approx. 40%
Colours: White
Drying: Approx 2 hours, sanding and recoatable: approx. 4 hours at +20 °C and 60% RH
Application: Optimum temperature for the product, subject and surroundings: 18-22 ° C and approx. 50% RH
Thinning: Water. Normally not to be diluted
Coverage: 6-8 m². Wet film 125-150 µm
Tools: Airless or Airmix. Optimal RF approx. 50%
Mal-Code:

