

Product Description

Water based interior base stain on a combination of acrylics and alkyds.
Fro wood og wood based products. Can be used with or without a clear topcoat.

Directions for use

Surface must be clean firm and sustainable.
Wood moisture should not exceed 20% RH
Any resin exudations to be removed and be after dried with appropriate thinner.
The product is thoroughly stirred prior to use.
Optionally diluted with water to spraying viscosity.

Cleaning instructions

Cleaning with clean water, preferably added a little detergent, immediately after use.

Safety & environment

Personal protection equipment must be used. For information regarding safety, health and environment see Material Safety Data Sheet (MSDS) at www.bj.dk.

Remarks

When used in dipping- or flow-coat systems it is important that the treated surfaces have a slope of approx. 20°. For longer periods of inactivity the system should be emptied and cleaned. The tapped product is filtered and kept in well closed containers.

In case of unacceptable development of foam, when dipping or flow-coating, add 50 ml. of 183 DK Defoamer to each 100 Lt. DK2

Technical data

Binder:	Combination of acrylic and alkyd
Type:	
Gloss:	
Vol. dry:	Approx. 15%
Colours:	Clear, can be tinted in transparent shades
Drying:	Approx. 2 hours at 20 °C and 65% RH, paintable when dry
Application:	Optimum temperature for the product, subject and location: 18-22 °C and R/F approx. 50%
Thinning:	For dipping and flow-coat adjust viscosity to 13-14 sec/DIN4
Coverage:	Approx. 10 m ² /ltr on planed wood
Tools:	Dipping, flow-coating, spray and brush
Mal-Code:	00-1 (1993)

